

Beständigkeitsliste / Resistance Table

CRASSUS

be smart. be a Problemlöser.

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
(o)-Chlorphenol	(o)-Chlorophenol	-	X	-	X	A	A	-	-
(p)-Cymene	(p)-Cymene	-	X	-	X	A	A	-	-
1,2-Diaminoethan	1,2-Diaminoethane	-	A	-	B	X	A	-	-
1,4-Dihydroxybenzol	1,4-Dihydroxybenzene	-	B	-	X	X	A	-	-
1-Butanethiol	1-Butanethiol	-	X	-	X	A	A	-	-
1-Hexadecanol	1-Hexadecanol	-	A	-	A	-	A	-	-
2-Methylpentan	2-Methylpentane	-	X	-	A	A	A	-	-
2-Propanon (Aceton)	2-Propanone (Acetone)	-	A	-	X	X	A	-	-
2-Propen-1-ol	2-Propene-1-ol	-	A	-	B	A	A	-	-
3,1-Dichlorpropen	3,1-Dichlorpropene	-	X	-	X	-	A	-	-
3-Methylpentan	3-Methylpentane	-	X	-	A	A	A	-	-
Abgase (Fortsetzung Chlorwasserstoff)	Waste Gas (cont. Hydrogen Chloride)	A	A	-	B	A	A	-	-
Abgase (Fortsetzung Kohlenmonoxid)	Waste Gas (cont. Carbon Monoxide)	A	A	-	A	A	A	-	-
Abgase (Fortsetzung Nitrous Dämpfe)	Waste Gas (cont. Nitrous Fumes)	A	A	-	-	A	A	-	-
Abgase (Fortsetzung Schwefeldioxid)	Waste Gas (cont. Sulfur Dioxide)	A	A	-	B	A	A	-	-
Abgase (Fortsetzung Schwefelsäure)	Waste Gas (cont. Sulfuric Acid)	A	A	-	X	A	A	-	-
Abgase (Kont. Kohlendioxid)	Waste Gas (cont. Carbon Dioxide)	A	A	-	A	A	A	-	-
Abgase (Kont. Wasserstofffluorid)	Waste Gas (cont. Hydrogen Fluoride)	A	A	-	A	A	A	-	-
Abwasser	Sewage	A	A	A	A	A	A	A	A
Acetaldehyd	Acetaldehyde	X	B	-	X	X	A	-	-
Acetamide	Acetamide	-	A	-	A	X	A	-	-
Aceton	Acetone	X	A	-	X	X	A	-	-
Acetophenon	Acetophenone	-	A	-	X	X	A	-	A
Acetylaceton	Acetylacetone	-	A	-	X	X	A	-	A
Acetylchlorid	Acetylchloride	-	X	-	X	A	A	-	-
Acetylen	Acetylene	-	B	-	A	A	-	-	-
Acetylen Gas	Acetylene Gas	A	A	-	A	A	A	-	-
Acetylentetrabromid	Acetylene Tetrabromide	-	A	-	X	A	A	-	-
Acrolein	Acrolein	-	A	-	C	X	A	-	-
Acrylnitril	Acrylonitrile	-	X	-	X	X	A	-	A
Adipic Aciddiethylester	Adipic Aciddiethylester	-	A	-	X	X	A	-	-
Adipic Säure	Adipic Acid	A	A	-	A	A	A	-	-
Aero Lubriplate	Aero Lubriplate	-	X	A	A	A	A	-	-
Aero safe 2300	Aero safe 2300	X	A	-	X	X	A	-	-
Aero safe 2300 W	Aero safe 2300 W	X	A	-	X	X	A	-	-
Aero Shell 1 AC Fett	Aero Shell 1 AC Grease	B	X	-	A	A	A	-	-
Aero Shell 17 Fett	Aero Shell 17 Grease	B	X	-	A	A	A	-	-
Aero Shell 7 A Fett	Aero Shell 7 A Grease	B	X	-	A	A	A	-	-
Aero Shell 750	Aero Shell 750	B	X	-	B	A	A	-	-
Aero Shell Fluid 4	Aero Shell Fluid 4	B	X	-	A	A	A	-	-
Aerozene 50 (50%Hydrazin, 50% UDMH)	Aerozene 50 (50%Hydrazine, 50% UDMH)	-	A	-	X	X	B	-	-
Alkohol (Methanol)	Alcohol (Methanol)	B	A	-	B	C	A	-	-
Alkohole (aliphatisch)	Alcohols, Aliphatic	-	B	-	A	-	-	-	-
Alkohole (aromatisch)	Alcohols, Aromatic	-	X	-	C	-	-	-	-
Alkyl Arylsulfonsäure	Alkyl Arylsulphonic Acid	-	A	-	C	X	A	-	-
Alkyl Benzen	Alkyl Benzene	-	X	-	X	A	A	-	-
Allyl Alkohol (2-Propene-1-ol)	Allyl Alcohol (2-Propene-1-ol)	-	A	-	B	B	A	-	-
Allyl Ketone	Allyl Ketone	-	A	-	X	X	A	-	-
Allylchlorid (3-Chlor-1-Propen)	Allyl Chloride (3-Chloro-1-Propene)	-	X	-	X	-	A	-	A
Aluminium Hydroxidlösung	Aluminium Hydroxide Solution	A	A	-	A	A	A	-	-
Aluminium-Acetat	Aluminium Acetat	-	A	-	B	X	A	-	-
Aluminiumbromid	Aluminium Bromide	A	A	A	A	A	A	-	-
Aluminiumchloridlösung	Aluminum Chloride Solution	A	A	-	A	A	A	-	-
Aluminiumfluorid	Aluminium Fluoride	A	A	A	A	A	A	A	A
Aluminium-Kaliumsulfatlösung	Aluminium-Potassiumsulfate Solution	A	A	-	-	-	A	-	-
Aluminiumnitrat	Aluminium Nitrate	A	A	A	A	A	A	A	A
Aluminiumphosphat	Aluminium Phosphate	A	A	-	A	A	A	-	-

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Aluminiumsulfat	Aluminium Sulfate	A	A	A	A	A	A	A	A
Aluminiumsulfatlösung	Aluminum Sulphate Solution	A	A	-	A	A	A	-	-
Ambrex 33 (Mobil)	Ambrex 33 (Mobile)	-	X	-	A	A	A	-	-
Ambrex 830 (Mobil)	Ambrex 830 (Mobile)	-	X	-	A	A	A	-	-
Ameisensäure	Formic Acid	A	B	A	X	X	A	A	A
Aminoessigsäure	Aminoacetic Acid	-	A	-	B	A	A	A	A
Ammoniak (flüssig)	Ammonia (liquid)	-	A	-	B	X	A	-	-
Ammoniak (Gas 65°C)	Ammonia, Gas 65°C	-	B	-	C	X	-	-	-
Ammoniak (Gas)	Ammonia (gas)	-	A	-	A	X	A	-	-
Ammoniak (Gas, heiß)	Ammonia (gas, hot)	-	B	-	X	X	A	-	-
Ammoniak (Gas, kalt)	Ammonia, Gas (Cold)	-	A	-	A	X	-	-	-
Ammoniak (in Wasser)	Ammonia, In water	-	A	-	B	B	-	-	-
Ammoniak (wasserfrei)	Ammonia, anhydrous	-	A	-	A	X	A	-	-
Ammoniak (wässrige Lösung)	Ammonia, aqueous Solution	-	A	-	C	X	A	-	-
Ammoniak-Lithium	Ammonia-Lithium	-	B	-	B	X	A	-	-
Ammoniaklösung	Ammonia Solution	-	A	-	B	X	A	-	-
Ammonium Nitrit	Ammonium Nitrite	-	A	-	A	-	A	-	-
Ammonium Thiocyanat	Ammonium Thiocyanate	-	A	-	A	-	A	-	-
Ammoniumacetat	Ammonium Acetate	-	A	-	A	X	A	A	A
Ammoniumcarbonat	Ammonium Carbonate	-	A	-	A	X	A	-	-
Ammoniumcarbonatlösung	Ammonium Carbonate Solution	-	A	-	X	-	A	-	-
Ammoniumchlorid	Ammonium Chloride	A	A	-	A	A	A	-	-
Ammoniumchloridlösung	Ammonium Chloride Solution	A	A	-	A	-	A	-	-
Ammoniumfluorid	Ammonium Fluoride	-	A	-	A	B	A	-	-
Ammoniumhydroxid	Ammonium Hydroxide	-	A	-	X	X	A	A	A
Ammoniumhydroxidlösung	Ammonium Hydroxide Solution	-	A	-	X	X	A	-	-
Ammoniumnitratlösung	Ammonium Nitrate Solution	-	A	-	A	-	A	-	-
Ammoniumphosphat, Monobasic, Dibasic, Tribasic	Ammonium Phosphate, Monobasic, Dibasic, Tribasic	-	A	-	A	-	A	-	-
Ammoniumsulfatlösung	Ammonium Sulfate Solution	A	A	-	A	X	A	-	-
Ammoniumsulfid	Ammonium Sulfide	-	A	A	B	X	A	A	A
Amyl Alkohol	Amyl Alcohol	A	A	-	B	B	A	-	-
Amyl Borate	Amyl Borate	-	X	-	A	-	A	-	-
Amyl Naphtalene	Amyl Naphtalene	-	X	-	X	A	A	-	-
Amylacetat	Amyl Acetate	X	A	-	X	X	A	-	-
Amylchlorid	Amyl Chloride	-	X	-	X	A	A	-	-
Ananassaft	Pineapple Juice	A	A	-	A	A	A	-	A
Anderol L-774	Anderol L-774	-	X	-	A	A	A	-	-
Aniinchlorhydrat	Aniline Chlorohydrate	-	B	-	B	B	A	-	-
Anilin	Aniline	-	X	-	X	B	-	-	-
Anilin Flüssigkeit	Aniline Liquid	-	A	-	X	X	A	-	-
Anisole	Anisole	-	X	-	X	X	A	-	-
Antimonchlorid	Antimony Chloride	A	A	A	A	A	A	-	-
Antimonchlorid (trocken)	Antimony Chloride, dry	A	A	-	A	A	A	-	-
Apfelsäure	Malic Acid	A	B	A	A	A	A	-	-
Apfelwein	Cider	A	A	-	A	B	A	-	-
Aqua Regia (Salpetersäure/Salzsäure)	Aqua Regia (Nitric Acid/Hydrochloric Acid)	-	X	-	X	X	B	-	-
Argon Gas	Argon Gas	A	A	-	A	A	A	-	-
Aromatische Brennstoffe (bis zu 50% Aromatisch)	Aromatic Fuels (up to 50% Aromatic)	-	X	-	A	A	A	-	-
Aromatische Kohlenwasserstoffe (100% Aromatisch)	Aromatic Hydrocarbons (100% Aromatic)	-	X	-	X	A	A	-	-
Arsensäure	Arsenic Acid	A	A	A	A	A	A	A	A
Arsensäure (Arsenlösung)	Arsenic Acid, Solution	A	A	-	A	A	A	-	-
Asphalt (Emulsion)	Asphalt, Emulsion	B	X	-	B	A	A	-	-
ASTM Test Kraftstoff A	ASTM Test Fuel A	A	X	-	A	A	A	-	-
ASTM Test Kraftstoff B	ASTM Test Fuel B	C	X	-	A	A	A	-	-
ASTM Test Kraftstoff C	ASTM Test Fuel C	X	X	-	B	A	A	-	-
ASTM-Öl IRM 902	ASTM-Oil IRM 902	A	X	-	A	A	A	-	-
ASTM-Öl IRM 903	ASTM-Oil IRM 903	A	X	-	A	A	A	-	-

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
ASTM-Öl Nr.1	ASTM-Oil No.1	A	X	-	A	A	A	-	-
Äther	Ether	-	C	-	X	X	A	-	-
Ätherische Öle	Essential Oils	X	X	-	X	B	A	-	-
ATM-Brake Fluid (Glykolbasis)	ATM-Brake Fluid (Glycolbased)	X	A	-	X	X	A	-	-
Aumine, primär (wie Methyl, Ethyl, Propyl, Allyl)	Amines, primary (such as Methyl, Ethyl, Propyl, Allyl)	X	A	-	X	X	A	-	-
Automatikgetriebeöl	Automatic-Transmission Fluid	A	X	-	A	A	A	-	-
Bariumcarbonat	Barium Carbonate	A	A	A	A	A	A	A	A
Bariumchloridlösung	Barium Chloride Solution	A	A	-	A	A	A	-	-
Bariumhydroxidlösung	Barium Hydroxide Solution	A	A	-	A	A	A	-	-
Bariumnitratlösung	Barium Nitrate Solution	A	A	-	A	A	A	-	-
Bariumsulfat	Barium Sulfate	A	A	-	A	A	A	-	-
Bariumsulfidlösung	Barium Sulfide Solution	A	A	-	A	A	A	-	-
Batteriesäure (Schwefelsäure verdünnt)	Battery Acid (Sulfuric Acid diluted)	-	A	-	X	A	A	-	-
Baumwollöl	Cotton Oil	B	C	-	A	A	A	-	-
Baumwollsaatöl	Cottonseed Oil	B	X	-	A	A	A	-	-
Benzaldehyd	Benzaldehyde	X	B	-	X	X	A	-	-
Benzin (100 Oktan)	Gasoline, 100 Octane	C	X	-	A	A	A	-	-
Benzin (130 Oktan)	Gasoline, 130 Octane	C	X	-	A	A	A	-	-
Benzin (Alkohol Mix)	Gasoline/Alcohol Mix	C	X	-	B	B	A	-	-
Benzin (aromatisch)	Gasoline, Aromatic	C	X	-	A	A	A	-	-
Benzin (Benzin)	Benzine (Gasoline)	C	X	-	A	A	A	-	-
Benzin (bleifrei)	Gasoline, Lead Free	C	X	-	A	A	-	-	-
Benzin (Ethyl und reguläre)	Gasoline, Ethyl and Regular	C	X	-	A	A	A	-	-
Benzin (mit Mercaptan)	Gasoline, with Mercaptan	C	X	-	A	A	A	-	-
Benzin (raffiniert)	Gasoline, Refined	C	X	-	A	A	A	-	-
Benzin (sauer)	Gasoline, Sour	C	X	-	A	A	A	-	-
Benzin e 50/Benzol 30/Ethanol 20	Benzine 50/Benzene 30/Ethanol 20	C	X	-	X	B	A	-	-
Benzin e 50/Benzol 50	Benzine 50/Benzene 50	C	X	-	X	B	A	-	-
Benzin e 60/Benzen 40	Benzine 60/Benzene 40	C	X	-	X	B	A	-	-
Benzin e 70/Benzol 30	Benzine 70/Benzene 30	C	X	-	B	A	A	-	-
Benzin e80/Benzol 20	Benzine 80/Benzene 20	C	X	-	B	A	A	-	-
Benzin für Kraftfahrzeuge	Automotive Gasoline	C	X	-	A	A	A	-	-
Benzin, Reg	Gasoline, Reg	C	X	-	A	A	-	-	-
Benzoessäure,lösung	Benzoic Acid, Solution	-	B	-	B	A	A	-	-
Benzol (Benzol)	Benzol (Benzene)	X	X	-	X	A	A	-	-
Benzolsulfonsäure	Benzenesulfonic Acid	-	-	A	X	A	A	-	A
Benzophenon	Benzophenone	-	B	-	-	A	A	-	-
Benzylalkohol	Benzyl Alcohol	-	B	-	X	A	A	-	-
Benzylchlorid	Benzyl Chloride	-	X	-	X	A	A	-	-
Bernsteinsäure	Succinic Acid	A	A	A	A	A	A	A	A
Bier	Beer	A	A	A	A	A	A	A	A
Biphenyl	Biphenyl	-	X	-	X	A	A	-	-
Bitumen	Bitumen	-	X	A	X	A	A	A	A
Bleiacetatsalzlösung	Lead Acetate Salt Solution	-	A	-	C	X	A	-	-
Bleiarsenat	Lead Arsenate	-	A	-	A	-	A	-	-
Blechlösung	Bleach Solution	-	A	-	X	A	A	-	-
Bleichpulverlösung	Bleaching Powder Solution	-	A	-	C	A	A	-	-
Bleinitrat	Lead Nitrate	A	A	A	A	A	A	-	-
Bleinitratlösung	Lead Nitrate Solution	-	A	-	A	-	A	-	-
Bleisulfat	Lead Sulfate	B	A	A	B	A	A	-	A
Borax (Natriumborat)	Borax (Sodiumborate)	-	A	-	B	A	A	-	-
Borax Lösungen	Borax Solutions	-	A	-	B	B	A	-	-
Borsäure	Boric Acid	A	A	A	A	A	A	A	A
Bremsflüssigkeiten (auf Mineralölbasis)	Brake Fluids (based on mineral oil)	B	-	-	A	A	A	-	-
Bremsflüssigkeiten (basierend auf Glykolether)	Brake Fluids (based on glycol ether)	B	A	-	X	X	A	-	-
Brom	Bromine	X	X	-	X	B	A	-	A
Bromdampf	Bromine Vapour	-	X	-	X	B	A	-	-

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Bromlösung in Wasser	Bromine Solution in Water	-	X	-	X	A	A	-	-
Bromobenzol	Bromobenzene	-	X	-	X	A	A	-	-
Bromochlorotrifluoroethan	Bromochlorotrifluoroethan	-	X	-	X	A	A	-	-
Bromwasser	Bromine Water	-	-	-	-	A	-	-	-
Bunkeröl	Bunker Oil	-	X	-	B	A	A	-	-
Butadien	Butadiene	-	X	-	X	B	A	-	A
Butan	Butane	-	X	-	A	A	A	A	A
Butandiol	Butandiol	A	A	-	A	X	A	-	A
Butanol (Butylalkohol)	Butanol, (Butyl Alcohol)	A	A	A	A	A	-	-	A
Butanole	Butanole	A	B	-	A	A	A	-	-
Butantriol	Butantriol	A	A	-	A	A	A	-	-
Butene	Butene	-	X	-	B	A	A	-	-
Buthylphenol	Buthylphenol	-	X	-	X	B	A	-	-
Butter	Butter	A	B	-	A	A	A	A	A
Buttermilch	Buttermilk	A	A	-	A	A	A	-	A
Buttersäure	Butyric Acid	A	X	-	B	A	A	-	-
Buttersäure-Butylester	Butyric Acid Butyl Ester	-	B	-	X	B	A	-	-
Butyl Alkohol	Butyl Alcohol	A	A	-	A	A	A	-	-
Butyl Amin	Butyl Amine	-	-	-	X	X	A	-	-
Butyl Carbitol	Butyl Carbitol	-	A	-	X	C	A	-	-
Butyl Cellosolve	Butyl Cellosolve	-	A	-	C	X	A	-	-
Butyl Diglycol	Butyl Diglycol	A	A	-	A	A	A	-	-
Butyl Phthalat	Butyl Phthalate	-	A	-	X	X	A	-	-
Butyl Pyrocatechol	Butyl Pyrocatechol	-	B	-	X	A	A	-	-
Butyl Stearate	Butyl Stearate	-	X	-	B	A	A	-	-
Butylacetat	Butyl Acetate	X	C	-	X	X	A	-	-
Butylbenzoat	Butylbenzoate	-	A	-	X	A	A	-	A
Butylen	Butylene	-	X	-	B	A	A	-	-
Butylether	Butylether	-	X	-	X	X	A	-	-
Butyraldehyd	Butyraldehyd	X	B	-	X	X	A	-	-
Calcium Silikate	Calcium Silikate	A	A	-	A	A	A	-	-
Calciumacetat	Calcium Acetate	A	A	A	B	X	A	-	A
Calciumbisulfat	Calcium Bisulfate	A	A	-	A	A	A	-	-
Calciumbisulfidlösung	Calcium Bisulfide Solution	A	A	-	B	B	A	-	-
Calciumcarbonat	Calcium Carbonate	A	A	-	A	A	A	-	-
Calciumcarbonat-Aufschlammung	Calcium Carbonate Slurry	A	A	-	A	A	A	-	-
Calciumchlorid	Calcium Chloride	A	A	-	A	A	A	A	A
Calciumchlorid (65°C)	Calcium Chloride 65°C	A	A	-	A	A	-	-	-
Calciumchlorid (Salzlösung)	Calcium Chloride, brine	A	A	-	A	A	A	-	-
Calciumcyanid	Calcium Cyanide	A	A	A	A	-	A	-	-
Calciumhydroxid-Lösung	Calcium Hydroxide Solution	A	A	-	A	A	A	-	-
Calcium-Hypochlorit-Lösung	Calcium Hypochlorite Solution	A	A	-	C	A	A	-	-
Calciumnitrat	Calcium Nitrate	A	A	-	A	A	A	-	-
Calciumoxid	Calcium Oxide	A	A	-	A	A	A	A	A
Calciumphosphat-Schlämme	Calcium Phosphate Slurry	A	A	-	A	A	A	-	-
Calciumsulfat	Calcium Sulfate	A	A	-	A	A	A	-	-
Calciumsulfid	Calcium Sulfide	A	A	A	A	A	A	-	A
Calciumsulfit	Calcium Sulfite	A	A	A	A	A	A	-	-
Calciumthiosulfat	Calcium Thiosulfate	A	A	A	B	A	A	-	-
Caliche Lösung (Natriumnitrat)	Caliche Solution (Sodium Nitrate)	-	A	-	B	A	A	-	-
Carbitol	Carbitol	-	B	-	B	B	A	-	-
Carbolineum	Carbolineum	-	B	-	B	A	A	-	A
Carbolsäure (Penole)	Carbolic Acid (Penole)	-	B	-	X	A	A	-	-
Carbonsäuren	Carboxylic Acids	A	A	-	A	A	A	-	-
Cellosolve (2-Etho-Yethanol)	Cellosolve (2-Etho-yethanol)	X	B	-	X	X	A	-	-
Celluloseacetat	Celluloseacetat	-	B	-	A	X	A	-	-
Chile Salpêtre (Natriumnitrat)	Chile Salpêtre (Sodium Nitrate)	-	A	-	B	A	A	-	-

Beständigkeitsliste / Resistance Table

CRASSUS

be smart, be a Problemlöser.

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Chinawood Oil	Chinawood Oil	-	X	-	A	A	A	-	-
Chlor (flüssig)	Chlorine, liquid	-	B	-	X	A	A	-	-
Chloraceton	Chloroacetone	-	A	A	X	X	A	-	-
Chlorbenzol	Chlorobenzene	X	X	-	X	B	A	-	-
Chlordioxid	Chlorine Dioxide	X	C	-	X	A	B	-	-
Chloressigsäure	Chloroacetic Acid	X	A	-	X	X	A	-	-
Chloressigsäure Ethylester	Chloroacetic Acid Ethylester	X	X	-	X	A	A	-	-
Chlorgas (wasserfrei)	Chlorine gas, Anhydrous	-	A	-	C	A	A	-	-
Chlorgas Trocken X	Chlorine Gas Dry X	X	X	-	X	-	-	-	-
Chlormethylether	Chloromethyl Ether	X	C	-	X	X	A	-	-
Chloroacetaldehyd	Chloroacetaldehyde	X	A	-	X	X	B	-	-
Chloroamin	Chloroamine	A	A	-	A	X	A	-	-
Chlorobromomethan	Chlorobromomethane	X	B	-	X	B	A	-	-
Chlorobutadien	Chlorobutadiene	X	X	-	X	B	A	-	-
Chloroform	Chloroform	X	X	-	X	B	A	-	-
Chloronaphthalin	Chloronaphthalene	X	X	-	X	A	A	-	-
Chlorothene	Chlorothene	X	X	-	X	B	A	-	-
Chlorotoluol	Chlorotoluene	X	X	-	X	A	A	-	-
Chlorsäure	Chloric Acid	X	B	-	X	B	A	-	-
Chlorsulfonsäure	Chlorosulfonic Acid	X	C	-	X	X	A	-	-
Chlorwasser	Chlorine Water	X	B	-	X	A	A	A	A
Chlorwasserstoffgas	Hydrogen Chloride Gas	X	A	-	X	A	A	-	-
Chrome Alum	Chrome Alum	A	A	-	A	A	A	-	-
Chromsäure	Chromic Acid	-	C	-	X	A	A	-	-
Chromsäure (38°C)	Chromic Acid 38°C	-	C	-	X	C	-	-	-
Chromschwefelsäure	Chromo sulfuric Acid	-	X	-	X	A	A	A	-
CIP-Flüssigkeiten (alkalisch)	CIP fluids, alkaline	-	A	-	X	X	A	-	-
CIP-Flüssigkeiten (sauer)	CIP fluids, acidic	-	A	-	X	B	A	-	-
Coca-Cola	Coca-Cola	A	A	-	A	B	A	-	-
Cresol	Cresol	-	X	-	X	A	A	-	-
Crontonaldehyd	Crontonaldehyde	-	A	-	X	X	A	-	-
Cumene	Cumene	-	X	-	X	A	A	-	-
Cupric Sulphate	Cupric Sulphate	-	A	-	A	A	-	-	-
Cyaninsäurelösung	Cyanic Acid Solution	-	A	-	B	A	A	-	-
Cyansäure	Cyanic Acid	-	A	-	B	A	A	-	-
Cyclohexan	Cyclohexane	C	X	-	A	A	A	-	-
Cyclohexanole	Cyclohexanole	-	X	-	B	A	A	-	-
Cyclohexanon	Cyclohexanone	-	X	-	X	X	A	-	-
Cyclohexylamin	Cyclohexylamine	-	C	-	X	X	A	-	-
DDT Lösungen (Kerosin-Lösungsmittel)	DDT Solutions (Kerosene Solvent)	-	X	-	A	A	A	-	-
DDT Lösungen (Toluol-Lösungsmittel)	DDT Solutions (Toluene Solvent)	-	X	-	X	A	A	-	-
Decalin (Decahydronaphtalen)	Decalin (Decahydronaphtalene)	-	X	-	X	A	A	-	-
Decane	Decane	-	X	-	A	A	A	-	-
Dextrin	Dextrin	A	A	-	A	A	A	A	A
Dextrose	Dextrose	A	A	-	A	A	A	-	-
Diaceton	Diacetone	-	A	-	-	X	A	-	-
Diaceton-Alkohol	Diacetone Alcohol	X	A	-	X	X	A	-	-
Diamylamin	Diamylamine	X	A	-	X	X	A	-	-
Diazinone	Diazinone	X	X	-	X	B	A	-	-
Dibenzyl Sebacate	Dibenzyl Sebacate	X	B	-	X	B	A	-	-
Dibenzylether	Dibenzyl Ether	X	B	-	X	C	A	-	A
Dibrommethylbenzol	Dibromomethylbenzene	X	X	-	X	A	A	-	-
Dibromodifluormethan	Dibromodifluoromethane	X	B	-	X	-	A	-	-
Dibutyl Ether	Dibutyl Ether	X	X	-	X	X	A	-	-
Dibutyl Sebacate	Dibutyl Sebacate	X	B	-	X	B	A	-	-
Dibutylamin	Dibutylamine	X	X	-	X	X	A	-	-
Dibutylphthalat	Dibutyl Phthalate	X	B	-	X	C	A	-	-

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Dichlorbutylen	Dichlorobutylene	X	X	-	X	B	A	-	-
Dichloressigsäure	Dichloro Acetic Acid	X	X	-	X	X	A	A	A
Dichloressigsäure Methylester	Dichloro Acetic Acid Methylester	X	A	-	X	X	A	-	-
Dichlorethan	Dichloroethane	X	X	-	X	B	A	-	-
Dichlorethylen	Dichloroethylene	X	X	-	X	B	A	-	-
Dichlormethan	Dichloromethane	X	X	-	X	B	A	-	-
Dichlorobutan	Dichlorobutane	B	X	-	B	A	A	-	-
Dichloro-Iso-Propylenether	Dichloro-iso-propylene ether	X	X	-	X	X	A	-	-
Dichloropentan	Dichloropentane	X	X	-	X	A	A	-	-
Dichlorobenzen	Dichlorobenzene	X	X	-	X	A	A	-	-
Dicyclohexylamin	Dicyclohexylamine	X	X	-	X	X	A	-	-
Diesekraftstoff	Diesel Fuel	A	X	-	A	A	A	-	A
Dieselöl	Diesel Oil	A	X	-	A	A	A	A	A
Dieselöl (65°C)	Diesel Oil 65°C	A	X	-	A	A	-	-	-
Diethanolamin	Diethanolamine	X	B	-	X	X	A	-	-
Diethyl Amin	Diethyl Amin	X	B	-	X	X	A	-	-
Diethyl Maleat	Diethyl Maleate	-	A	-	C	X	A	-	-
Diethyl-Aniline	Diethyl Aniline	-	A	-	X	X	A	-	-
Diethylbenzol	Diethyl Benzene	-	X	-	X	A	A	-	-
Diethylcarbonat	Diethyl Carbonate	X	X	-	X	A	A	-	-
Diethylen Triamin	Diethylene Triamine	-	A	-	X	X	A	-	-
Diethylenglykol	Diethylene Glycol	A	A	A	A	A	A	-	A
Diethylether	Diethyl Ether	-	C	-	X	X	A	-	-
Diethylformaldehyd	Diethyl Formaldehyde	-	A	-	X	X	A	-	-
Diethylhydrazin	Diethyl Hydrazine	-	A	-	C	X	A	-	-
Diethyl-Sebacate	Diethyl Sebacate	-	B	-	X	B	A	-	-
Diethylsulfat	Diethyl Sulfate	-	-	A	X	X	A	-	-
Diglykolsäure	Diglycolic Acid	-	A	-	X	A	A	-	-
Dihexyl Phthalsäure Ester	Dihexyl Phthalic Acid Ester	-	-	-	X	X	A	-	-
Dihydroxy Tartarsäure (Tartarsäure)	Dihydroxy Tartaric Acid (Tartaric Acid)	-	B	-	A	A	A	-	-
Di-Isobutyl Ketone	Di-Isobutyl Ketone	-	A	-	X	X	A	-	-
Di-Isobutylene	Di-Isobutylene	-	X	-	B	A	A	-	-
Di-Isooctyl-Sebacate	Di-Isooctyl Sebacate	-	B	-	X	B	A	-	-
Di-Isopropyl Keton	Di-Isopropyl Ketone	-	A	-	X	X	A	-	-
Di-Isopropylbenzol	Di-Isopropyl Benzene	-	X	-	X	A	A	-	-
Dimethyl Ketone	Dimethyl Ether	-	A	-	X	X	A	-	-
Dimethyl Phenol	Dimethyl Formamide	-	X	-	X	X	A	-	-
Dimethyl-Amin	Dimethyl Amine	-	B	-	X	X	A	-	-
Dimethyl-Anilin	Dimethyl Aniline	-	B	-	X	X	A	-	-
Dimethylbutan	Dimethyl Ketone	-	X	-	A	A	A	-	-
Dimethylether	Dimethyl Phenol	-	A	-	X	X	A	-	A
Dimethylformamid	Dimethyl Phthalate	-	B	-	X	X	B	-	-
Dimethylhydrazin	Dimethylbutane	-	A	-	B	X	A	-	-
Dimethylphthalat	Dimethyl Hydrazine	-	B	-	X	B	A	-	-
Dinitro Toluen	Dinitro Toluene	-	X	-	X	X	A	-	-
Dinitrogenoxid	Dinitrogene Oxid	-	B	-	A	A	A	-	-
Diocetyl Sebacate	Diocetyl Sebacate	-	B	-	X	B	A	-	-
Diocetyl-Amin	Diocetyl Amine	-	A	-	X	X	A	-	-
Diocetylphthalat (DOB)	Diocetyl Phthalate (DOB)	X	B	-	X	B	A	-	-
Dioxane	Dioxane	-	B	-	X	X	A	-	-
Dioxolane	Dioxolane	-	B	-	X	X	A	-	-
Dipentene	Dipentene	-	X	-	B	A	A	-	-
Diphenyl	Diphenyl	-	X	-	X	A	A	-	-
Diphenylether	Diphenyl Ether	-	X	-	X	B	A	-	-
Diphenyloxid	Diphenyle Oxide	-	X	-	X	A	A	-	-
Dipropylenglykol	Dipropylene Glycol	-	B	-	B	B	A	-	A
Dithionit	Dithionite	-	A	-	B	A	A	-	-

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Divinylbenzol	Divinyl Benzene	-	X	-	X	A	A	-	-
DMT (Dimethylterephthalat)	DMT (Dimethyl Terephthalate)	-	A	-	X	A	A	-	-
DNCB (Dinitrochlorbenzol)	DNCB (Dinitrochlorobenzene)	-	X	-	X	A	A	-	-
Dodecanol	Dodecanol	-	B	-	B	A	A	-	-
Dowtherm A	Dowtherm A	A	X	-	X	A	A	-	-
Dowtherm E	Dowtherm E	-	X	-	X	A	A	-	-
Duodecanol (Laurylalkohol)	Duodecanol (Laurylalkohol)	-	B	-	B	A	A	-	-
Eisenchlorid (65°C)	Ferric Chloride 65°C	-	A	-	A	A	-	-	-
Eisenchloridlösung	Ferric Chloride Solution	A	A	-	A	A	A	-	-
Eisennitrate	Ferric Nitrates	A	A	-	A	A	A	-	-
Eisensulfat (Eisen (III) -vitrinol)	Ferric Sulfate (Ferric Vitrinol)	A	A	-	A	A	A	-	-
Eisensulfatlösung	Ferric Sulfate Solution	A	A	-	A	A	A	-	-
Epichlorhydrin	Epichlorhydrin	-	B	-	X	X	A	-	A
Erdgas	Natural Gas	-	X	-	A	A	A	-	-
Erdnussöl	Peanut Oil	A	X	-	A	A	A	A	A
Erdöl	Petroleum	A	X	-	A	A	A	A	A
Essig	Vinegar	B	A	A	B	B	A	A	A
Essigester (Ethylacetat)	Acetic Ester (Ethyl Acetate)	-	-	-	X	X	-	-	-
Essigsäure (30%)	Acetic Acid 30%	A	A	-	C	C	A	-	-
Essigsäure (96-99,5%, eiskalt)	Acetic Acid, 96-99,5% (Glacial)	B	B	-	X	X	A	-	-
Essigsäureanhydrid	Acetic Anhydride	A	B	-	X	X	A	-	-
Essigsäurechlorid	Acetic Acid Chloride	-	X	-	X	A	A	-	-
Essigsäuredämpfe	Acetic Acid Vapors	-	A	-	X	X	A	-	-
Ethan	Ethane	-	X	-	A	A	A	-	-
Ethanol-Amin	Ethanol Amine	-	B	-	C	X	A	-	-
Ethylacetat	Ethyl Acetate	X	C	-	X	X	A	-	-
Ethylacrylat	Ethylacrylate	-	-	-	X	X	A	-	-
Ethylalkohol, Ethanol	Ethyl Alcohol, Ethanol	A	A	-	A	X	A	-	-
Ethylbenzol	Ethyl Benzene	-	X	-	X	B	A	-	A
Ethylbromid	Ethyl Bromide	-	X	-	B	A	A	-	-
Ethylcellulose	Ethyl Cellulose	-	B	A	B	X	A	-	-
Ethylchloracetat	Ethylchloroacetate	-	B	-	B	A	A	-	-
Ethylchlorid	Ethylchloride	-	B	-	X	B	A	-	-
Ethylen	Ethylene	-	X	-	A	A	A	-	-
Ethylen Chlorohydrin	Ethylene Chlorohydrin	-	B	-	X	X	A	-	-
Ethylenbromid	Ethylene Bromide	-	C	-	X	A	A	-	-
Ethylenchlorid	Ethylene Chloride	-	B	-	-	B	A	-	-
Ethylen-Diamin	Ethylene Diamine	-	A	-	X	X	A	-	-
Ethylendibromid	Ethylene Dibromide	-	X	-	X	A	A	-	-
Ethylendichlorid	Ethylene Dichloride	X	X	-	X	A	A	-	-
Ethylenglycol (65°C)	Ethylene Glycol 65°C	-	A	-	A	A	-	-	-
Ethylenglycol (Frostschutzmittel)	Ethylene Glycol (Antifreeze)	A	A	A	A	A	A	A	A
Ethylenglycol Ethylether (Cellosolve)	Ethylene Glycol Ethylether (Cellosolve)	B	B	-	X	X	A	-	-
Ethylenoxid	Ethylene Oxide	-	B	A	X	X	A	A	A
Ethylensilikat	Ethylene Silicate	A	A	A	A	A	A	A	A
Ethylentrichlorid	Ethylene Trichloride	-	C	-	X	B	A	-	-
Ethylether	Ethyl Ether	C	X	-	C	X	-	-	-
Ethylhexanol	Ethyl Hexanole	A	A	A	A	A	A	A	A
Ethyloxalat	Ethyl Oxalate	X	A	A	X	A	A	-	-
Ethylpentachlorbenzol	Ethyl Pentachlorobenzene	X	X	-	X	A	A	-	-
Ethylpyridin	Ethyl Pyridine	X	A	-	X	C	A	-	-
Ethylsulfat (Diethylsulfat)	Ethyl Sulfate (Diethyl Sulfate)	X	A	-	X	X	A	-	-
Fette (tierisch/pflanzlich)	Fats (animal/vegetable)	A	X	-	A	A	A	-	-
Fettsäuren	Fatty Acids	B	X	-	B	A	A	A	A
Fischöl	Fish Oil	A	X	-	A	A	A	-	-
Flugbenzin	Aviation Gasoline	A	X	-	A	A	-	-	-
Fluor	Fluorine	X	X	-	X	X	B	-	A

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Fluorbenzen	Fluorobenzene	X	X	-	X	B	A	-	-
Fluorosilicisäure	Fluorosilicic Acid	B	A	-	B	A	A	-	-
Flüssiggas	Liquified Petroleum Gas	A	X	-	A	A	-	-	-
Flusssäure (heiß)	Hydrofluoric Acid (hot)	X	X	-	X	X	A	-	-
Flusssäure (kalt)	Hydrofluoric Acid (cold)	X	B	-	X	B	A	-	-
Formaldehyd (Formalin-Lösung)	Formaldehyde (Formalin-Solution)	X	A	-	C	X	A	-	-
Formaldehyd (Methanal)	Formaldehyde (Methanal)	X	A	-	B	B	A	-	-
Formamid	Formamide	-	A	A	B	B	A	-	A
Fotografisches Entwicklungsbad	Photographic Developing Bath	-	B	-	A	A	A	-	-
Freon 11	Freon 11	-	X	-	A	B	B	-	-
Freon 112	Freon 112	-	X	-	B	B	A	-	-
Freon 113	Freon 113	A	X	-	A	B	B	-	-
Freon 114	Freon 114	-	A	-	A	B	B	-	-
Freon 114 B2	Freon 114 B2	-	X	-	B	B	B	-	-
Freon 115	Freon 115	-	A	-	A	B	B	-	-
Freon 12	Freon 12	-	B	-	B	B	B	-	-
Freon 13	Freon 13	-	A	-	A	B	B	-	-
Freon 13 B1	Freon 13 B1	-	A	-	A	B	B	-	-
Freon 134 a	Freon 134 a	-	A	-	-	-	B	-	-
Freon 14	Freon 14	-	A	-	A	B	B	-	-
Freon 142 b	Freon 142 b	-	A	-	A	X	B	-	-
Freon 152 a	Freon 152 a	-	A	-	A	X	B	-	-
Freon 21	Freon 21	-	X	-	X	X	A	-	-
Freon 218	Freon 218	-	A	-	A	A	B	-	-
Freon 22	Freon 22	-	A	-	X	X	B	-	-
Freon 31	Freon 31	-	A	-	X	X	B	-	-
Freon 32	Freon 32	-	A	-	A	X	B	-	-
Freon 502	Freon 502	-	A	-	B	B	B	-	-
Freon BF	Freon BF	-	X	-	B	A	B	-	-
Freon C316	Freon C316	-	A	-	A	-	B	-	-
Freon C318	Freon C318	-	A	-	A	B	B	-	-
Freon MF	Freon MF	-	X	-	B	B	B	-	-
Freon PCA	Freon PCA	-	X	-	A	B	B	-	-
Freon TA	Freon TA	-	A	-	A	X	B	-	-
Freon TC	Freon TC	-	B	-	A	A	B	-	-
Freon TF	Freon TF	-	X	-	A	A	B	-	-
Freon TMC	Freon TMC	-	B	-	B	A	B	-	-
Freon T-P35	Freon T-P35	-	A	-	A	A	B	-	-
Freon TWD602	Freon TWD602	-	A	-	B	A	B	-	-
Frischwasser 82°C	Water, Fresh 82°C	A	A	A	A	A	A	A	A
Fruchtsäfte	Fruit Juices	-	A	A	B	B	B	A	A
Fumarsäure	Fumaric Acid	-	-	A	A	A	A	-	-
Furan	Furan	-	X	-	X	X	A	-	-
Furfural (Furfurylaldehyd)	Furfural (Furfurylaldehyde)	-	-	-	C	-	A	-	-
Furfurylalcohol	Furfurylalcohol	-	-	-	-	-	A	-	-
Gallussäure	Gallic Acid	B	B	-	A	A	A	-	-
Gasöl	Gas Oil	A	X	-	A	A	A	-	A
Geister	Spirits	A	A	-	A	A	A	-	-
Gelatine	Gelatin	A	A	-	A	A	A	A	A
Gemüsesäfte	Vegetable Juices	A	A	A	A	A	A	A	A
Generatorgas	Generator Gas	-	X	-	A	A	A	-	-
Glaubers Salz	Glauber's Salt	A	A	-	B	B	A	-	-
Glukose (wässrig)	Glucose, aqueous	A	A	A	A	A	A	A	A
Glukoselösung	Glucose solution	A	A	A	A	A	A	A	A
Glycerin	Glycerol	A	A	A	A	A	A	A	A
Glycerin (Glycerin)	Glycerin (Glycerol)	-	A	-	A	A	A	-	-
Glycerin Chlorohydrin	Glycerol Chlorohydrin	-	B	-	X	B	A	-	-

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Glycerintriacetat (Triacetin)	Glycerol Triacetate (Triacetin)	-	A	-	B	X	A	-	-
Glyceroltrirat (Nitroglycerin)	Glycerol Trinitrate (Nitroglycerin)	-	A	-	X	A	A	-	-
Glycin	Glycine	-	A	-	B	A	A	-	-
Glykolsäure	Glycolic Acid	-	A	-	A	B	A	-	-
Harnstoff	Urea	A	A	A	A	A	A	A	A
HEF-3	HEF-3	-	X	-	B	A	A	-	-
Hefe	Yeast	A	A	A	A	A	A	A	A
Heliumgas	Helium Gas	A	A	A	A	A	A	A	A
Heptan	Heptane	-	X	-	A	A	A	-	A
Hexachloracetone	Hexachloro Acetone	-	A	-	X	X	A	-	-
Hexachlorcyclohexan (Lindan)	Hexachloro Cyclohexane (Lindane)	-	X	-	-	A	A	-	-
Hexachloro Butadien	Hexachloro Butadiene	-	X	-	X	A	A	-	-
Hexafluorosilisäure	Hexafluorosilicic Acid	-	B	-	B	B	A	-	-
Hexaldehyd	Hexaldehyd	-	A	-	X	X	A	-	-
Hexalin (Cyclohexanol)	Hexalin (Cyclohexanol)	-	X	-	A	A	A	-	A
Hexamine	Hexamine	-	A	-	X	X	A	-	-
Hexan	Hexane	A	X	-	A	A	A	A	A
Hexanal (Capronaldehyd)	Hexanal (Capronaldehyde)	-	B	-	-	X	A	-	-
Hexanetriol	Hexanetriol	A	A	A	A	A	A	A	A
Hexene	Hexene	-	X	-	B	A	A	-	-
Hexylalkohol	Hexyl Alcohol	-	B	-	A	A	A	-	-
Hochofengas	Blast Furnace Gas	-	X	-	X	A	A	-	-
Holzalkohol (Methanol)	Wood Alcohol (methanol)	-	X	-	A	X	-	-	-
Holzgeist	Wood Spirit	-	A	-	B	C	A	-	-
Hydrazin	Hydrazine	-	A	-	B	C	A	-	A
Hydrazin Hydrathydrate	Hydrazine Hydrate	-	A	-	B	C	A	-	-
Hydrobromsäure	Hydrobromic Acid	-	A	-	X	A	A	-	-
Hydrochinon	Hydroquinone	-	B	-	X	X	A	-	-
Hydrocyansäure	Hydrocyanic Acid	-	A	-	B	A	A	-	-
Hydrogensulfitaugung	Hydrogensulfite Leach	-	A	-	X	A	A	-	-
Hydroxyessigsäure	Hydroxy Acetic Acid	-	A	-	X	X	A	-	-
Hydroxylamin	Hydroxylamine	A	A	A	A	A	A	A	A
Hydroxylaminsulfat	Hydroxylamine Sulfate	A	A	A	A	A	A	A	A
Hypochlorsäure	Hypochlorous Acid	-	B	-	X	A	A	-	-
Inländische Heizöle	Domestic Fuel Oils	A	X	-	A	A	A	-	-
Iodoform	Iodoform	-	A	-	-	A	A	-	-
Iso-Butan	Iso-Butane	-	X	-	A	A	A	-	-
Iso-Butyl-Alkohol	Iso-Butyl Alcohol	-	A	-	B	B	A	-	-
Iso-Butylen	Iso-Butylene	-	X	-	A	A	A	-	-
Iso-Butyl-Methylketon	Iso-Butyl Methyl Ketone	-	A	-	X	X	A	-	-
Iso-Butyraldehyd	Iso-Butyraldehyde	-	A	-	X	X	A	-	-
Iso-Cyanat	Iso-Cyanate	-	A	-	-	-	A	-	-
Iso-Dodecane	Iso-Dodecane	-	X	-	A	A	A	-	-
Iso-Octane	Iso-Octane	B	X	-	A	A	A	-	-
Iso-Pentane	Iso-Pentane	-	X	-	A	A	A	-	-
Iso-Propyl-Alkohol	Iso-Propyl-Alcohol	A	A	-	B	A	A	-	-
Iso-Propyl-Benzol	Iso-Propyl-Benzene	-	X	-	X	A	A	-	-
Iso-Propyl-Chlorid	Iso-Propyl-Chloride	-	X	-	X	A	A	-	-
Iso-Propyl-Ether	Iso-Propyl-Ether	-	A	-	X	X	A	-	-
Iso-Propyl-Acetat	Iso-Propyl-Acetate	-	B	-	X	X	A	-	-
Jet Fuel JP3	Jet Fuel JP3	-	X	-	A	A	A	-	-
Jet Fuel JP4	Jet Fuel JP4	-	X	-	A	A	A	-	-
Jet Fuel JP5	Jet Fuel JP5	-	X	-	A	A	A	-	-
Jet Fuel JP6	Jet Fuel JP6	-	X	-	A	A	A	-	-
Jod	Iodine	-	B	-	B	A	A	-	-
Jod-Tinktur	Iodine tincture	-	B	-	B	A	A	-	-
JP3 (Kraftstoff)	JP3 (Fuel)	-	X	-	A	A	A	-	-

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
JP4 (Kraftstoff)	JP4 (Fuel)	-	X	-	A	A	A	-	-
JP5 (Kraftstoff)	JP5 (Fuel)	-	X	-	A	A	A	-	-
JP6 (Kraftstoff)	JP6 (Fuel)	-	X	-	A	A	A	-	-
JPX (Kraftstoff)	JPX (Fuel)	-	X	-	A	X	A	-	-
Kaffee	Coffee	A	A	A	A	A	A	A	A
Kaffee-Extrakt	Coffee Extract	A	A	A	A	A	A	A	A
Kakaobutter	Cocoa Butter	-	X	-	A	A	A	-	-
Kalium dichromate	Potassium Dichromate	A	A	A	A	A	A	A	A
Kaliumacetat	Potassium Acetate	A	A	-	B	B	A	A	A
Kalium-Aluminiumsulfat	Potassium Aluminium Sulfat	A	A	-	-	-	A	-	-
Kalium-Bicarbonit	Potassium Bicarbonite	A	A	A	A	A	A	A	A
Kaliumbisulfat	Potassium Bisulfate	A	A	A	A	A	A	A	A
Kaliumborat	Potassium Borate	A	A	A	A	A	A	A	A
Kaliumbromate	Potassium Bromate	A	A	A	A	A	A	A	A
Kaliumbromid	Potassium Bromide	A	A	A	A	A	A	A	A
Kaliumcarbonat	Potassium Carbonate	A	A	A	A	A	A	A	A
Kaliumchlorat	Potassium Chlorate	A	A	A	X	A	A	A	A
Kaliumchlorid	Potassium Chloride	A	A	A	A	A	A	A	A
Kaliumchromat	Potassium Chromate	A	A	-	B	A	A	-	-
Kaliumcyanid	Potassium Cyanide	A	A	A	A	A	A	A	A
Kaliumhydroxid (65°C)	Potassium Hydroxide 65°C	A	A	-	B	C	-	-	-
Kaliumhydroxid (Kaliumlye)	Potassium Hydroxide, Potassium Lye	A	A	-	B	X	A	-	-
Kaliumhydroxid (Lösung 50%)	Potassium Hydroxide (Solution 50%)	A	A	-	B	C	A	-	-
Kaliumhypochlorit (Javellewasser)	Potassium Hypochlorite (Javelle water)	B	B	-	B	A	A	-	-
Kaliumiodid	Potassium Iodide	A	A	A	A	A	A	A	A
Kaliumnitrat	Potassium Nitrate	-	A	-	B	A	A	-	-
Kaliumperchlorat	Potassium Perchlorate	-	A	-	X	A	A	A	A
Kaliumperfluoracetat	Potassium Perfluoroacetate	-	A	-	B	X	A	-	-
Kaliumpermanganat	Potassium Permanganate	-	A	-	X	A	A	A	A
Kaliumpersulfat	Potassium Persulfate	-	A	A	X	A	A	A	A
Kaliumphosphat	Potassium Phosphate	A	A	A	A	A	A	A	A
Kaliumsulfat	Potassium Sulfate	A	A	A	A	A	A	A	A
Kaliumsulfit	Potassium Sulfite	A	A	A	A	A	A	A	A
Kalkchlorid	Chloride of Lime	-	A	-	X	A	A	-	-
Kampfer	Campher	-	X	-	A	B	A	-	-
Kampferöl	Campher Oil	A	X	-	A	B	A	-	-
Kasein	Casein	-	B	-	A	A	A	-	-
Kerosin	Kerosene	A	X	-	A	A	A	A	A
Kesselspeisewasser	Boiler Feed Water	-	A	-	B	B	A	-	-
Ketchup	Ketchup	A	A	A	A	A	A	A	A
Kiefernöl	Pine Oil	-	X	-	B	A	A	-	-
Kieselsäure	Silicic Acid	A	A	A	A	A	A	A	A
Knochenöl	Bone Oil	A	X	-	A	A	A	-	A
Kobaltchlorit	Cobalt Chlorite	A	A	A	A	A	A	A	A
Kohlendioxid (nass)	Carbon Dioxide, wet	B	B	-	A	A	A	-	-
Kohlendioxid (trocken)	Carbon Dioxide, dry	B	B	-	A	A	A	-	-
Kohlenmonoxid	Carbon Monoxide	A	A	-	A	B	A	-	-
Kohlensäure	Carbonic Acid	A	A	A	A	A	A	A	A
Kohlenstoff Tetrachlorid	Carbon Tetrachloride	C	X	-	C	A	-	-	-
Kohlenstoffdisulfid	Carbon Disulfide	X	X	-	X	A	A	-	-
Kohlenteer	Coal Tar	B	X	-	B	B	A	-	-
Kokosfett	Coconut Grease	A	X	-	A	A	A	-	-
Kokosnuss (Fettsäure)	Coconut, Fatty Acid	A	X	-	A	A	A	-	-
Kokosöl	Coconut Oil	A	X	-	A	A	A	-	-
Koksofengas	Coke Oven Gas	-	X	-	X	A	A	-	-
Kupfer (I) -ammoniumacetat-Lösung	Cuprous Ammonia Acetate Solution	-	A	-	X	X	A	-	-
Kupfer Ammoniumacetat	Copper Ammonium Acetate	-	A	-	X	X	A	-	-

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Kupferacetatlösung	Copper Acetate Solution	-	B	-	X	X	A	-	-
Kupferchloridlösung	Copper Chloride, Solution	A	A	A	A	A	A	A	A
Kupfercyanid	Copper Cyanide	A	A	A	A	A	A	A	A
Kupferfluorid	Copper Fluoride	A	A	-	B	A	A	-	-
Kupfernitrat	Copper Nitrate	A	A	-	B	A	A	-	-
Kupfersulfat (Blue Vitriol) Lösung	Copper Sulfate (Blue Vitriol) Solution	A	A	A	A	A	A	A	A
Lachgas (N2O)	Laughing Gas (N2O)	B	B	-	A	A	A	-	-
Lactams	Lactams	X	X	-	X	X	A	-	-
Lanolin	Lanolin	X	X	-	A	A	A	-	-
Latex	Latex	A	A	A	A	A	A	A	A
Lavendelöl	Lavender Oil	X	X	-	B	A	A	-	A
Lebertran	Cod-liver Oil	B	B	-	A	A	A	-	A
Leinöl	Linseed Oil	C	C	-	A	A	A	-	-
Ligroin	Ligroin	X	X	-	A	A	A	-	-
Liköre	Liqueurs	A	A	A	A	A	A	A	A
Limettenmilch	Milk of Lime	A	A	-	X	B	A	-	-
Lindol	Lindol	A	A	-	X	X	A	-	-
Linolsäure	Linoleic Acid	X	X	-	B	A	A	-	-
Lithiumbromid-Salzlösung	Lithium Bromide Brine	A	A	A	A	A	A	A	A
Lithiumchlorid	Lithium Chloride	A	A	A	A	A	A	A	A
Lithiumhydroxid	Lithium Hydroxide	A	A	-	X	-	A	-	-
Luft	Air	A	A	A	A	A	A	A	A
Maganchloridlösung	Manganese Chloride (Solution)	A	A	A	A	A	A	A	A
Magnesiumacetatlösung	Magnesium Acetate Solution	A	A	-	X	X	A	-	-
Magnesiumchloridlösung	Magnesium Chloride Solution	A	A	A	A	A	A	A	A
Magnesiumhydroxidlösung	Magnesium Hydroxide (Solution)	A	A	-	B	B	A	-	-
Magnesiumsilikat (Talcum)	Magnesium Silicate (Talcum)	A	A	A	A	A	A	A	A
Magnesiumsulfat (Epsonsalze)	Magnesium Sulfate (Epson Salts)	A	A	A	A	A	A	A	A
Maisöl	Corn Oil	A	X	A	A	A	A	A	-
Maleinsäure	Maleic Acid	A	A	-	B	A	A	-	-
Maleisches Anhydrid	Maleic Anhydride	-	X	-	X	B	A	-	-
Margarine	Margarine	-	X	-	A	A	A	A	A
Maschinenöl (mineralisch)	Machinery Oil (mineral)	-	X	-	A	A	A	-	-
Mayonaise	Mayonaise	-	X	-	A	X	A	-	-
Meerwasser	Sea Water	A	A	-	A	B	A	-	-
Melasse	Molasses	A	A	A	A	A	A	A	A
Menthol	Menthol	-	B	A	B	A	A	-	A
Mercaptans	Mercaptans	-	A	-	X	X	A	-	-
Mesityloxid	Mesityl Oxide	-	A	-	X	X	A	-	-
Methacrylsäure	Methacrylic Acid	-	B	-	X	X	A	-	A
Methan	Methane	-	X	-	A	A	A	-	A
Methanal	Methanal	-	A	-	B	B	A	-	-
Methoxy Benzol	Methoxy Benzene	-	X	-	X	X	A	-	-
Methoxy Butanol	Methoxy Butanol	-	B	-	A	A	A	-	-
Methyl Butyl Keton	Methyl Butyl Ketone	-	A	-	X	X	A	-	-
Methyl Iso-Butyl Keton (MIBK)	Methyl Iso-Butyl Ketone (MIBK)	X	B	-	X	X	A	-	-
Methyl Iso-Propyl Keton	Methyl Iso-Propyl Ketone	-	A	-	X	X	A	-	-
Methylacetat	Methyl Acetate	-	A	-	X	X	A	-	-
Methylacetoacetat	Methyl Acetoacetate	-	A	-	X	X	A	-	-
Methylacrylat	Methyl Acrylate	-	B	-	X	X	A	-	-
Methylalkohol (Methanol)	Methyl Alcohol (Methanol)	-	A	-	B	C	A	-	-
Methylamin	Methyl Amine	-	A	-	X	X	A	-	-
Methyl-Anilin	Methyl Aniline	-	B	-	X	B	A	-	-
Methylbromid	Methyl Bromide	-	X	-	X	A	A	-	-
Methylcarbonat	Methyl Carbonate	-	X	-	X	X	A	-	-
Methylcellosolve	Methyl Cellosolve	-	B	-	X	X	A	-	-
Methylcellulose	Methyl Cellulose	-	B	A	B	B	A	-	-

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Methylchlorid	Methyl Chloride	-	B	-	X	B	A	-	-
Methylcyclopentan	Methyl Cyclopentane	-	X	-	X	B	A	-	-
Methylenchlorid	Methylene Chloride	X	X	-	X	B	A	-	-
Methylethylketon (MEK)	Methyl Ethyl Ketone (MEK)	-	B	-	X	X	A	-	-
Methylformate	Methyl Formate	-	B	-	X	X	A	-	-
Methylglycol	Methyl Glycol	-	B	-	X	X	A	-	-
Methylglycolacetat (Ethylenglykol)	Methyl Glycol Acetate (Ethylene glycol)	-	B	-	X	X	A	-	-
Methylmethacrylat	Methyl Methacrylate	-	X	-	X	X	A	-	-
Methylmethacrylsäureester	Methyl Methacrylic Acid Ester	-	X	-	X	X	A	-	-
Methyloleat	Methyl Oleate	-	B	-	X	A	A	-	-
Methylphenylether (Anisole)	Methyl Phenyl Ether (Anisole)	-	X	-	X	X	A	-	-
Methylpyrrolidon	Methyl Pyrrolidone	-	A	-	X	X	A	-	-
Methylsalicylat	Methyl Salicylate	-	B	-	X	-	A	-	A
Milch	Milk	A	A	A	A	A	A	A	A
Milchsäure	Lactic Acid	T	B	-	B	A	A	A	A
Mineralische Spirituosen	Mineral Spirits	-	X	-	A	A	A	-	-
Mineralöl	Mineral Oil	A	X	-	B	A	A	-	-
Monobromobenzen	Monobromobenzene	-	X	-	X	B	A	-	-
Monochlorbenzol	Monochlorobenzene	-	X	-	X	B	A	-	-
Monochloressigsäure	Monochloroacetic Acid	-	A	-	X	X	A	A	A
Monochloressigsäureethylester	Monochloroacetic Acid Ethyl Ester	-	B	-	X	X	A	-	-
Monoethanol-Amin	Monoethanol Amine	-	B	-	X	X	A	-	-
Mononitrochlorbenzol	Mononitrochlorobenzene	-	X	-	X	A	A	-	-
Morpholine	Morpholine	-	B	-	X	-	A	-	-
Muriasäure (HCl) (Salzsäure)	Muriatic Acid (HCl) (Hydrochloric Acid)	-	B	-	X	A	A	-	-
Muriasäure (HCl, verdünnt)	Muriatic Acid (HCl), diluted	-	A	-	B	A	A	-	-
Naphtha	Naphtha	-	X	-	X	A	A	A	A
Naphthalin	Naphthalene	-	X	-	X	A	A	-	-
Naphthensäure	Naphthenic Acid	-	X	-	B	A	A	-	-
Naphtolen ZD	Naphtolen ZD	-	X	-	B	A	A	-	-
Natriumacetat	Sodium Acetate	-	A	-	B	X	A	A	A
Natriumbenzoat	Sodium Benzoate	A	A	A	A	A	A	A	A
Natriumbicarbonatlösung	Sodium Bicarbonate Solution	A	A	A	A	A	A	A	A
Natriumbisulfatlösung	Sodium Bisulfate Solution	A	A	A	A	A	A	A	A
Natriumbisulfittlösung	Sodium Bisulfite Solution	A	A	A	A	A	A	A	A
Natriumborat (Borax)	Sodium Borate (Borax)	-	A	-	B	A	A	-	-
Natriumcarbonat (65°C)	Sodium Carbonate 65°C	-	A	-	A	A	-	-	-
Natriumcarbonat (Soda Asche)	Sodium Carbonate (Soda Ash)	A	A	A	A	A	A	A	A
Natriumcarbonatlösung	Sodium Carbonate Solution	A	A	A	A	A	A	A	A
Natriumchlorat	Sodium Chlorate	-	A	-	B	A	A	-	A
Natriumchlorid (Normales Salz)	Sodium Chloride (Common Salt)	A	A	A	A	A	A	A	A
Natriumchloridlösung	Sodium Chloride Solution	A	A	A	A	A	A	A	A
Natriumchlorit	Sodium Chlorite	-	A	-	X	A	A	-	-
Natriumcyanidlösung	Sodium Cyanide Solution	-	A	-	B	-	A	-	-
Natriumdichromat	Sodium Dichromate	-	A	-	B	A	A	A	A
Natriumfluorid	Sodium Fluoride	A	A	-	A	A	A	A	A
Natriumhydroxid	Sodium Hydroxide	A	A	-	B	C	A	-	-
Natriumhydroxid (65°C)	Sodium Hydroxide 65°C	-	A	-	B	C	-	-	-
Natriumhydroxid (Ätznatron)	Sodium Hydroxide, Caustic Soda	-	A	-	B	B	A	-	-
Natriumhydroxid (Ätznatron, 65°C)	Sodium Hydroxide Caustic Soda 65°C	-	A	-	B	C	-	-	-
Natriumhypochloritlösung	Sodium Hypochlorite Solution	-	A	-	B	A	A	-	-
Natriumnitrat	Sodium Nitrate	-	A	-	B	A	A	-	-
Natriumnitrit	Sodium Nitrite	-	A	A	X	A	A	A	A
Natriumperoxidlösung	Sodium Peroxide Solution	-	A	-	B	A	A	-	-
Natriumphosphat	Sodium Phosphate	A	A	A	A	A	A	A	A
Natriumsilikatlösung	Sodium Silicate Solution	A	A	A	A	A	A	A	A
Natriumsulfatlösung (Glauber-Salz)	Sodium Sulfate Solution (Glauber's Salt)	-	A	-	B	B	A	-	-

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Natriumsulhydratlösung	Sodium Sulphhydrate Solution	A	A	A	A	A	A	A	A
Natriumsulfid	Sodium Sulfide	B	A	A	B	A	A	A	A
Natriumsulfittlösung	Sodium Sulfite Solution	A	A	A	A	A	A	A	A
Natriumtetraboratlösung	Sodium Tetraborate Solution	B	A	-	B	A	A	-	-
Natriumthiosulfat (Antichlor)	Sodium Thiosulfate (Antichlor)	B	A	-	B	A	-	-	-
Neon Gas	Neon Gas	A	A	A	A	A	A	A	A
Nickelacetat	Nickel Acetate	B	A	-	B	X	A	-	-
Nickelchlorid	Nickel Chloride	A	A	A	A	A	A	A	A
Nickelnitrat	Nickel Nitrate	A	A	A	A	A	A	A	A
Nickelsulfat	Nickel Sulfate	A	A	A	A	A	A	A	A
Nitrating Säuren	Nitrating Acids	-	A	-	X	X	A	-	-
Nitro Benzol	Nitro Benzene	X	X	-	X	X	A	-	-
Nitro Methan	Nitro Methane	-	B	-	X	X	A	-	-
Nitro Propan	Nitro Propane	-	B	-	X	X	A	-	-
Nitro Toluene	Nitro Toluene	-	X	-	X	X	A	-	-
NitroGlycerin	Nitro Glycerin	-	A	-	X	A	A	-	-
NitroGlycol	Nitro Glycol	-	A	-	X	A	A	-	-
Nonanol	Nonanol	-	A	-	X	A	A	-	-
Nussöl	Nut Oil	-	X	-	A	A	A	-	-
Octadecane	Octadecane	-	X	-	A	A	A	-	-
Octane	Octane	-	X	-	B	A	A	-	-
Octanol (Octylalkohol)	Octanol (Octylalcohol)	-	A	-	B	A	A	-	-
Octylalkohol	Octylalcohol	-	B	A	B	A	A	-	A
Octylcresol	Octylcresol	-	X	-	C	B	A	-	-
Oktal	Octal	-	B	-	X	B	A	-	-
Öl von Terpentin	Oil of Turpentine	-	X	-	B	A	A	-	-
Olefin (roh)	Olefin, crude	-	X	-	A	A	A	-	-
Oleic Alkohol	Oleic Alcohol	A	A	A	A	A	A	A	A
Oleum (Schwefelsäure, 0 bis 50%)	Oleum (Sulfuric Acid, 0 to 50%)	-	A	-	X	A	A	-	-
Olivenöl	Olive Oil	A	X	-	A	A	A	-	A
Ölsäure	Oleic Acid	A	X	-	A	A	A	-	-
Ordentliches Fußöl	Neats Foot Oil	A	B	-	A	A	A	-	-
Ortho Dichloro Benzol	Ortho Dichloro Benzene	X	X	-	X	A	A	-	-
Oxalsäure	Oxalic Acid	B	A	-	B	A	A	-	-
Ozone	Ozone	A	B	-	X	A	A	-	-
Palmitinsäure	Palmitic Acid	B	C	A	B	A	A	A	A
Palmkernöl	Palm Kernel Oil	A	X	-	A	A	A	-	A
Palmöl	Palm Oil	A	X	-	A	A	A	-	A
Para Dichlorbenzol	Para Dichloro Benzene	X	X	-	X	A	A	-	-
Paraffin	Paraffin	A	X	-	A	A	A	-	-
Paraffinöl	Paraffin Oil	A	X	-	A	A	A	-	A
Pektin	Pectin	A	A	A	A	A	A	A	A
Penta Chloro Diphenyl	Penta Chloro Diphenyl	-	X	-	X	C	A	-	-
Penta Chloro Phenol	Penta Chloro Phenol	-	B	-	X	-	A	-	-
Pentane	Pentane	-	X	-	A	A	A	-	-
Pentanol	Pentanol	-	A	-	B	B	A	-	-
Perachlorethylen	Perachloroethylene	-	X	-	X	A	-	-	-
Perchlorethylen	Perchloro Ethylene	X	X	-	X	B	A	-	-
Perchlorsäure	Perchloric Acid	-	B	-	X	A	A	-	-
Petroleum Ether	Petroleum Ether	-	X	-	A	A	A	-	-
Pflanzliche Öle	Vegetable Oils	A	X	-	A	A	A	-	-
Phenol	Phenol	-	X	-	X	B	A	-	-
Phenol (52°C)	Phenol 52°C	-	C	-	X	A	-	-	-
Phenyl Hydrazin	Phenyl Hydrazine	-	X	-	X	B	A	-	-
Phenylbenzol	Phenyl Benzene	-	X	-	X	B	A	-	-
Phenylether	Phenyl Ether	-	X	-	X	X	A	-	-
Phosphin	Phosphine	-	A	-	X	B	A	-	-

Beständigkeitsliste / Resistance Table

CRASSUS

be smart. be a Problemlöser.

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Phosphorsäure	Phosphoric Acid	-	B	-	X	A	A	-	-
Phosphorsäure (45%)	Phosphoric Acid 45%	-	A	-	B	A	A	-	-
Phosphortrichlorid	Phosphorous Trichloride	-	A	-	X	A	A	-	A
Phthalsche Anhydrid	Phthalic Anhydride	-	A	-	-	-	A	-	-
Phthalsäure	Phthalic Acid	-	A	-	B	B	A	-	-
Picoline (alpha)	Picoline, alpha	-	A	-	-	X	A	-	-
Pikrinsäure (wässrige Lösung)	Picric Acid, Aqueous Solution	-	B	-	B	A	A	-	-
Pinene	Pinene	-	X	-	B	A	A	-	-
Piperidin	Piperidine	-	X	-	X	X	A	-	A
Polyvinylacetat	Polyvinyl Acetates	-	A	-	-	X	A	-	-
Propan	Propane	-	X	-	A	A	A	-	-
Propangas	Propane Gas	-	X	-	A	A	-	-	-
Propanol	Propanol	-	A	-	B	A	A	-	-
Propinylalkohol	Propinyl Alcohol	A	A	A	A	A	A	A	A
Propion Aldehyd	Propion Aldehyde	-	A	-	X	X	A	-	-
Propionsäure	Propionic Acid	-	B	-	A	A	A	-	-
Propylacetat	Propyl Acetat	-	B	-	X	X	A	-	-
Propylacetone	Propyl Acetone	-	A	-	X	X	A	-	-
Propyl-Amin	Propyl Amine	-	X	-	X	X	A	-	-
Propylen	Propylene	-	X	-	X	A	A	-	A
Propylendichlorid	Propylene Dichloride	-	X	-	X	-	A	-	-
Propylenglykol	Propylene Glycol	A	A	A	A	A	A	A	A
Propylenoxid	Propylene Oxide	-	B	-	X	X	A	-	A
Propylnitrat	Propyl Nitrate	-	A	-	X	X	A	-	-
Pyridin	Pyridine	-	B	-	X	B	A	A	A
Pyrrole	Pyrrole	-	X	-	X	X	A	-	-
Quecksilber	Mercury	A	A	A	A	A	A	A	A
Quecksilberchloridlösung	Mercuric Chloride Solution	A	A	A	A	A	A	A	A
Quecksilbernitrat	Mercury Nitrate	-	A	A	A	-	A	A	A
Rapsöl	Rapeseed Oil	A	X	-	B	A	A	-	-
Reinigungslösungen	Detergent Solutions	A	A	-	A	B	-	-	-
Rindertalg	Beef Tallow	-	X	-	A	A	A	-	A
Rizinusöl	Castor Oil	A	B	-	A	A	A	-	-
Rohöl	Crude Oil	B	X	-	B	A	A	A	A
Rohrzucker-Saft	Cane Sugar Sap	A	A	A	A	A	A	A	A
Rosin (Kolophonie)	Rosin (Colophony)	A	A	A	A	A	A	A	A
Röstgas (trocken)	Roast Gas (dry)	A	A	A	A	A	A	A	A
Saccharosesaft	Sucrose Sap	A	A	A	A	A	A	A	A
Salicylsäure	Salicylic Acid	-	A	-	B	A	A	-	-
Salpetersäure (10%, 79°C)	Nitric Acid 10% 79°C	A	C	-	X	X	-	-	-
Salpetersäure (30% bis 70%)	Nitric Acid 30% to 70%	-	X	-	X	C	-	-	-
Salpetersäure (dämpfen)	Nitric Acid, fuming	-	X	-	X	B	A	-	-
Salpetersäure (konzentriert)	Nitric Acid, concentrated	-	X	-	X	B	A	-	-
Salpetersäure (roter Rauch)	Nitric Acid, Red Fuming	X	X	-	X	X	-	-	-
Salzsäure (100%)	Hydrochloric Acid 100%	B	C	-	-	C	-	-	-
Salzsäure (37%, 52°C)	Hydrochloric Acid 37% 52°C	A	B	-	C	A	-	-	-
Salzsäure (Muriatic Acid, 37%)	Hydrochlorique Acid (Muriatic Acid) 37%	A	B	-	X	A	A	-	-
Salzwasser 62°C	Water, Salt 62°C	-	A	-	C	A	A	-	-
Sauerstoff (kalt)	Oxygen, Cold	-	A	-	B	A	-	-	-
Schmieröle	Lubricating Oils	A	X	-	A	A	-	-	-
Schwarzlauge	Black Liquor	-	B	A	B	B	A	-	-
Schwefel	Sulfur	A	A	-	X	A	A	A	A
Schwefelchlorid	Sulfur Chloride	-	X	-	X	A	A	-	-
Schwefeldioxid (gasförmig)	Sulfur Dioxide, gaseous	A	A	-	X	X	A	-	-
Schwefeldioxid (SO2)	Sulfur Dioxide (SO2)	A	A	-	X	B	A	-	-
Schwefeldioxid Flüssigkeit (wasserfrei)	Sulfur Dioxide Liquid (anhydrous)	A	A	-	X	X	A	-	-
Schwefelhexafluorid (SF6)	Sulfur Hexafluoride (SF6)	A	A	-	B	B	A	-	-

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Schwefelsäure	Sulfurous Acid	A	B	-	-	A	A	-	-
Schwefelsäure (0 bis 50%)	Sulfuric Acid (0 to 50%)	-	B	-	X	B	A	-	-
Schwefelsäure (25% / 50%, 38°C)	Sulphuric Acid, 25%/50% 38°C	-	-	-	X	-	-	-	-
Schwefelsäure (25%, 65°C)	Sulphuric Acid, 25% 65°C	-	B	-	X	A	-	-	-
Schwefelsäure (rauchend)	Sulphuric Acid, Fuming	-	X	-	X	X	-	-	-
Schwefelsäure (verdünnt)	Sulfuric Acid, diluted	-	A	-	B	A	A	-	-
Schwefelwasserstoff	Hydrogen Sulfide	A	C	-	X	X	A	A	A
Seifenlösung	Soap Solution	A	A	A	A	A	A	A	A
Silbercyanidlösung	Silver Cyanide Solution	-	X	-	X	A	A	-	-
Silbernitrat	Silver Nitrate	-	A	-	B	A	A	-	-
Silbersalze	Silver Salts	A	A	A	A	A	A	A	A
Siliciumdioxid	Silicon Dioxide	A	A	A	A	A	A	A	A
Silikonfett	Silicone Grease	A	A	A	A	A	A	A	A
Silikonöl	Silicone Oil	A	A	A	A	A	A	A	A
Skydrol (Hydraulikflüssigkeiten)	Skydrol Hydraulic Fluids	-	A	-	X	B	-	-	-
Skydrol 500	Skydrol 500	X	A	-	X	X	A	-	-
Skydrol 7000	Skydrol 7000	-	A	-	X	B	A	-	-
Soda (Natriumcarbonat)	Soda (Sodium Carbonate)	A	A	A	A	A	A	A	A
Sojabohnenöl	Soy Bean Oil	A	X	-	A	A	-	-	A
Spermacetin	Spermacetin	-	X	-	A	A	A	-	-
Spermaöl	Sperm Oil	-	B	-	A	A	A	-	-
Stärke	Starch	A	A	A	A	A	A	A	A
Stearinsäure	Stearic Acid	A	B	-	B	A	A	-	-
Stickstoffgas	Nitrogen Gas	A	A	A	A	A	A	A	A
Stickstofftetroxid	Nitrogen Tetroxide	-	X	-	X	X	-	-	-
Stoddard Lösungsmittel	Stoddard Solvent	-	X	-	A	A	A	-	-
Styrol	Styrene	-	X	-	X	A	A	-	-
Talg	Tallow	-	B	-	A	A	A	A	A
Talkum	Talcum	A	A	A	A	A	A	A	A
Tannenöl	Fir Oil	-	X	-	B	A	A	-	-
Tannine	Tannins	-	B	-	B	A	A	-	-
Teer	Tar	-	X	-	X	B	A	A	A
Terpentin	Turpentine	B	X	-	A	A	A	A	-
Tetrachlorethan	Tetrachloroethane	-	X	-	X	B	A	-	-
Tetrachlorethylen	Tetrachloroethylene	-	X	-	X	A	A	-	-
Tetrachlormethan	Tetrachloromethane	-	X	-	X	A	A	-	-
Tetraethyl-Blei	Tetraethyl Lead	-	X	-	B	A	A	-	-
Tetrahydrofuran	Tetrahydrofuran	X	X	-	X	X	A	-	-
Thionylchlorid	Thionyl Chloride	-	B	-	X	A	A	-	-
Thiophen	Thiophene	-	X	-	X	X	A	-	-
Tierische Fette	Animal Fats	A	B	-	A	A	A	A	A
Tinte	Ink	A	A	A	A	B	A	A	A
Titantetrachlorid	Titanium Tetrachloride	B	B	-	B	B	A	-	-
Toluene (Toluol)	Toluene (Toluol)	X	X	-	X	B	A	-	-
Transformatoröl	Transformer Oil	B	X	-	B	A	A	-	-
Triacetin (Glycerintriacetat)	Triacetin (Glycerine Triacetate)	B	A	-	B	X	A	-	-
Triarylphosphat	Triaryl Phosphate	X	A	-	X	A	A	-	-
Tributoxy Ethylphosphat	Tributoxy Ethyl Phosphate	X	B	-	X	B	A	-	-
Tributyl Marcaptane	Tributyl Marcaptane	X	X	-	X	A	A	-	-
Tributylphosphat	Tributyl Phosphate	X	B	-	X	X	A	-	-
Trichlorbenzol	Trichloro Benzene	-	X	-	-	A	A	-	-
Trichloressigsäure	Trichloroacetic Acid	-	B	-	B	X	A	A	A
Trichlor-Ethan	Trichloro Ethane	X	C	-	X	A	A	-	-
Trichlorethylen	Trichloro Ethylene	X	C	-	X	B	A	-	A
Trichlor-Ethylphosphat	Trichloro Ethyl Phosphate	-	-	-	X	X	A	-	-
Tricresylphosphat	Tricresyl Phosphate	C	B	-	X	B	A	-	-
Triethanolamin	Triethanolamine	A	A	-	-	-	A	-	-

Beständigkeitsliste / Resistance Table

A Exzellent / Excellent	B Gut / Good	C Bedingt / Limited	X Unbeständig / Unstable	- nicht getestet / not tested
--------------------------------	---------------------	----------------------------	---------------------------------	-------------------------------

Beschreibung (Deutsch)	Description (English)	Material							
		TPE	EPDM	SBR	NBR	FKM	FFKM	PVC	PP
Triethyl Boran	Triethyl Borane	-	-	-	-	A	A	-	-
Triethylaluminium	Triethylaluminium	-	X	-	-	B	A	-	-
Triethylglycol	Triethyl Glycol	A	A	A	A	A	A	A	A
Trifluor-Ethan	Trifluoro Ethane	-	X	-	X	A	A	-	-
Tri-Iso-Propylbenzol	Tri-Iso-Propyl Benzene	-	X	-	A	A	-	-	-
Trinatriumphosphatlösung	Trisodium Phosphate Solution	A	A	A	A	A	A	A	A
Trinitrotoluen (TNT)	Trinitrotoluene (TNT)	-	X	-	X	B	A	-	-
Trioctylphosphat	Trioctyl Phosphate	-	A	-	X	B	A	-	A
Vaseline	Vaseline	A	X	-	A	A	A	-	A
Vaselineöl	Vaseline Oil	A	X	-	A	A	A	-	-
Vinylacetat	Vinyl Acetate	-	-	-	-	-	A	-	-
Vinylchlorid (flüssig)	Vinyl Chloride, liquid	-	-	-	-	-	A	-	-
Vinylidenchlorid	Vinylidene Chloride	-	X	-	X	B	A	-	-
Wachsalkohol	Wax Alcohols	-	X	-	A	A	A	A	A
Wasser bis +135 °C / +275 °F	Water to +135 °C / +275 °F	A	A	-	X	C	A	-	-
Wasser bis +80 °C / +176 °F	Water to +80 °C / +176 °F	A	A	-	B	B	A	-	-
Wasserdampf < +140 °C / +284 °F	Water vapour < +140 °C / +284 °F	A	A	-	X	X	A	-	-
Wasserdampf > +140 °C / +284 °F	Water vapour > +140 °C / +284 °F	B	B	-	X	X	A	-	-
Wasserstoffbromid (wasserfrei)	Hydrogene Bromide, anhydrous	-	X	-	X	A	A	-	-
Wasserstofffluorid	Hydrogen Fluoride	-	B	-	X	-	A	-	-
Wasserstoffgas	Hydrogen, Gas	A	A	A	A	A	A	A	A
Wasserstoffperoxid (10%)	Hydrogen Peroxide 10%	-	X	-	C	-	-	-	-
Wasserstoffperoxid (90%)	Hydrogen Peroxide 90%	-	C	-	X	B	-	-	-
Wasserstoffperoxid (konzentriert)	Hydrogen Peroxide, concentrated	-	X	-	X	B	A	-	-
Wein und Whiskey	Wine + Whiskey	A	A	-	A	A	A	A	A
Weinsäure	Tartaric Acid	A	B	-	A	A	A	-	-
Weißer Likör	White Liquor	-	X	-	A	-	-	-	-
Weißes Öl	White Oil	-	X	-	A	A	-	-	-
Xenon	Xenon	A	A	A	A	A	A	A	A
Xylidine (aromatische Amine)	Xylidines (aromatic Amines)	-	B	-	X	X	A	-	-
Xylol (Xylol)	Xylene (Xylol)	X	X	-	X	B	A	-	-
Zeolithe	Zeolites	A	A	A	A	A	A	A	A
Zinkacetat	Zinc Acetate	-	A	-	B	B	A	-	-
Zinkchloridlösungen	Zinc Chloride Solutions	A	A	-	A	A	A	A	A
Zinksulfat	Zinc Sulfate	A	A	-	A	A	A	A	A
Zinn (II) -chlorid-Lösung	Stannic Chloride Solution	A	A	-	A	A	A	A	A
Zitronenöl	Citrous Oils	B	X	-	B	A	A	-	-
Zitronensaft	Lemon Juice	A	A	A	A	A	A	-	A
Zitronensäure	Citric Acid	A	A	A	A	A	A	A	A
Zuckerlösung	Sugar Solutions	A	A	A	A	A	A	A	A
Zuckerrübensaft	Beet Sugar Sap	A	A	A	A	A	A	A	A